

STANDARD SPECIFICATION FOR: 80/20 Media with Fire Retardant

Fiber Composition	4.5 oz/sy
Cellulose	80%
Polyester	20%
Overall Caliper	0.028 in
Corrugation Depth	0.016 in
Permeability	14 cfm
Max Pore Diameter	50 microns
Resin Content	39%
Mullen Burst	
As is, Dry	43.6 psi
As is, Wet	35.8 psi
Finish: Fire Retardant	
Particle Efficiency by Weight:	
0.5 micron	99.80%
1.0 micron	99.90%
2.0 micron	100%