

STANDARD SPECIFICATION FOR:	80/20 Media with Fire Retardant
Fiber Composition	4.5 oz/sy
Cellulose	80%
Polyester	20%
Overall Caliper	0.028 inch
Corrugation Depth	0.016 inch
Permeability	14 cfm/sf/min
Max Pore Diameter	50 microns
Resin Content	39%
Mullen Burst	
As is, Dry	43.6 PSI
As is, Wet	35.8 PSI
Finish	Fire Retardant
Filtration Efficiency	MERV 11