

STANDARD SPECIFICATION FOR:	Nanofiber with Fire Retardant
Fiber Composition	4.5 oz/sy
Cellulose	80%
Polyester	20%
Overall Caliper	0.028 inch
Corrugation Depth	0.016 inch
Permeability	25 cfm/sf/min
Max Pore Diameter	45 microns
Bust Strength	≥ 58 PSI
Mullen Burst	
As is, Dry	43.6 PSI
As is, Wet	35.8 PSI
Finish	Nanofiber with Fire Retardant
Filtration Efficiency	MERV 15